

# LOCAL PLY SE DHOKA MAT KHAIE, GHAR LAIYE.

## SAINIK 710

by  CENTURYPLY®


### ASLI WATERPROOF PLY



LOCAL PLY



SAINIK 710



**BOILING  
WATER PROOF**

**BORER AND  
TERMITE PROOF**

**8 YEAR  
WARRANTY**

**Sainik 710**, is produced from rotary-cut, smooth veneers, sourced from specially selected eco-friendly timber.

- Bend resistant
- Accordance to IS:710
- Chemically treated for borer and termite proof
- More durable & cost effective
- 8-Year Warranty\*
- GLP
- Green Building certified
- A unique and first in class one India one price product
- CenturyPly in house manufactured product

\*Check the Warranty Terms & Conditions



**8 YEAR  
WARRANTY**

## TECHNICAL SPECIFICATIONS\*

### PLYWOOD

Moisture Content (%)	8 - 12
Adhesion of Plies (Water Resistant)	Excellent
Preservative Treatment	Two Tier Treatment: 1. Glue Line Protection 2. Finished panels are treated with ACC (Acid Copperchrome Compound)
Specific Gravity	> 0.560
Water Absorption (%)	< 5
Screw holding strength (Kgf)	> 150
Nail holding strength (Kgf)	> 85
Static Bending Strength (N/mm <sup>2</sup> )	> 48 > 35
Modulus of rupture (MOR): Along the grain: Across the grain:	> 4800 > 2300
Modulus of elasticity (MOE): Along the grain: Across the grain:	> 4800 > 2300

### BLOCKBOARD

Moisture Content (%)	10 - 12
Adhesion of plies	Excellent
Preservative Treatment	Three Tier Treatment: 1. Treated fillers 2. Glue Line Protection 3. Finished panels are treated with ACC (Acid Copperchrome Compound)
Specific Gravity	> 0.50
Screw holding strength (Kgf)	> 125
Nail holding strength (Kgf)	> 65
Modulus of Elasticity (N/mm <sup>2</sup> )	> 5100
Modulus of Rupture (N/mm <sup>2</sup> )	> 52

\*Conditions apply