



Why Everest Agni Rodhak Plywood?

- BWP Ply with Fire Retardant properties
- 300% money back guarantee*
- Borer & termite proof
- Slow burning
- Low flammability & lesser smoke
- STR8 technology
- Smooth surface & calibrated

31
years
warranty
*conditions apply

Technical Specifications

Test	Unit	IS:710	Agni Rodhak
Moisture Content	%	Max 20%	7-10%
Glue she strength	N/m2	1350	1500
Tensile Strength	N/m2	84.5	95
Modulus of Elasticity (MoE)	N/m2	7500	8400
Modulus of Rapture (MoR)	N/m2	50	59
Modulus of Rigidity	N/m2	588	655
Screw Holding capacity	kg	250	>250
Nail Hoilding Capacity	kg	150	>150

Retention of Chemicals	kg/m3	12	13.5
Specific Gravity	kg/m3	NA	0.75

Test	Unit	IS:5509	Agni Rodhak
Flamanibility	Minute	Min 30 Minutes	36.10
Flame Penetration	Minute	Min(15* Thikness/6) Minutes	78.20
Rate of Burning	Minute	Min 20 Minutes	25.60



A quality product from

Everest Ply and Veneers Pvt. Ltd.

Corporate Identity Number U51431WB1997PTC085083

Follow us on



@everestply



Everest Ply



Everest Ply

e-mail: enquiry@everestply.com | Toll-free No.: 1800 4252 130



99000 99130



99000 99130

www.everestply.com