



Why Club MR?

- 100% Gurjan Face
- Termite Proof
- Borer Free
- Structurally Balanced
- Core Jointer Technology
- Machine Composted Core
- Selected Hardwood Used

11
YEARS
WARRANTY
*conditions apply

Technical Specifications

Test	Unit	IS 303	Club MR
Moisture Content	%	5-15	8-12
Glue shere strength	N/m ²	1000	1100
Tensile Strength	N/m ²	60	85
Modulus of Elasticity (MoE)	N/m ²	4000	4500
Modulus of Rapture (MoR)	N/m ²	30	32.8
Modulus of Rigidity	N/m ²	408	420.9
Screw Holding capacity	Kg	150	>150
Nail Hoilding Capacity	Kg	80	>100
Retention of Chemicals	Kg/m ³	8	>8.2
Specific Gravity	Kg/m ³	NA	



A quality product from

Everest Ply and Veneers Pvt. Ltd.

Corporate Identity Number U51431WB1997PTC085083

Follow us on



@everestply



Everest Ply



Everest Ply

e-mail: enquiry@everestply.com | Toll-free No.: 1800 4252 130



99000 99130



99000 99130

www.everestply.com